

Comparison of the Fatigue Behavior of Copper Alloys

Drs. Brad Lerch and David Ellis

Presented at MS&T05
Pittsburgh, PA
September 25-28, 2005



Glenn Research Center at Lewis
Field



Life Prediction Branch:
where failure is not an option

Introduction



Thrust Chamber

- Develop advanced copper alloys for rocket engine applications
- Desire: high thermal conductivity, good creep strength, adequate fatigue strength.
- Advanced alloy – GRCop-84
Developed at NASA-GRC,
commercially available.



Glenn Research Center at Lewis
Field

Life Prediction Branch:
where failure is not an option



Objective

- Characterize fatigue behavior of GRCop-84 in various forms
- Compare fatigue of GRCop-84 to existing high conductivity copper alloys

AMZIRC

Narloy-Z

Glidcop

Cu-1Cr

Cu-1Cr-0.1Zr



Glenn Research Center at Lewis
Field



Life Prediction Branch:
where failure is not an option

Material

GRCop-84 Extruded bar

Reference data - for Reuseable Launch Vehicle program

Tested in as-extruded and in simulated braze conditions

GRCop-84 Large Extrusion

Tested in as-extruded condition

L, L-T and S-T orientations

GRCop-84 0.04" thick sheet

Tested after 500 °C/ 30 min heat treatment

L and L-T orientations



Glenn Research Center at Lewis
Field



Life Prediction Branch:
where failure is not an option

Material

AMZIRC Extruded bar

Tested in as-extruded and in simulated braze conditions

Narloy-Z cast and hot rolled plate 1.5" thick

Tested in heat treated condition:

927 C/2 hrs + 482 C/4 hrs




Glenn Research Center at Lewis
Field



Life Prediction Branch:
where failure is not an option

Experimental Details


- 6 inch long, dogbone-shaped samples
- Gage diameter 0.25"
- Specimens cycled in strain control
- Strain ratio = -1
- Strain rate = 0.002/sec.
- Temp. = 20, 400, 600 °C
- Environment: argon, air
- Failure defined as two pieces
- Sheet samples tested with both buckling guides and unconstrained



GRCop-84 Large Extrusion

Fatigue lives of both forms are similar

Fatigue Life for Extruded Bar and Large Extrusion GRCop-84





Glenn Research Center at Lewis
Field

Life Prediction Branch:
where failure is not an option



GRCop-84 Large Extrusion, L-T Orientation



Cr₂Nb stringers responsible for low life of S-T samples



Glenn Research Center at Lewis
Field




Life Prediction Branch:
where failure is not an option

GRCop-84 Large Extrusion

The large extrusion is slightly softer at elevated temperatures

Cyclic Stress-Strain Data for Extruded Bar and Large Extrusion GRCop-84



Glenn Research Center at Lewis
Field


Life Prediction Branch:
where failure is not an option



GRCop-84 0.04" Thick Sheet

Sheet material has shorter life than extruded bar

Fatigue Life for Extruded and Sheet GRCop-84



Glenn Research Center at Lewis
Field


Life Prediction Branch:
where failure is not an option



GRCop-84 0.04" Thick Sheet

Sheet material is cyclically stronger than bar form

Cyclic Stress-Strain Data for Extruded and Sheet GRCop-84



Glenn Research Center at Lewis
Field


Life Prediction Branch:
where failure is not an option



AMZIRC

AMZIRC has a similar life to GRCop-84 at moderate temperatures

Comparison of AMZIRC and Extruded GRCop-84



Glenn Research Center at Lewis
Field


Life Prediction Branch:
where failure is not an option



AMZIRC

Contrary to GRCop-84, braze condition affects strength of AMZIRC

Comparison of AMZIRC with Extruded GRCop-84



Glenn Research Center at Lewis
Field


Life Prediction Branch:
where failure is not an option



Narloy-Z

Narloy-Z has similar fatigue lives at moderate temperatures

Comparison of Extruded Narloy-Z and GRCop-84



Glenn Research Center at Lewis
Field


Life Prediction Branch:
where failure is not an option



Narloy-Z

Narloy-Z has similar strength to GRCop-84 at moderate temperatures

Comparison of Extruded Narloy-Z and GRCop-84




Glenn Research Center at Lewis
Field

Life Prediction Branch:
where failure is not an option



Life Comparison – All Alloys

Comparison of Fatigue Lives at 25 °C as a Function of Total Strain Range



GRCop-84 has similar fatigue lives at 25 °C




Glenn Research Center at Lewis
Field

Life Prediction Branch:
where failure is not an option



Life Comparison – All Alloys



GRCop-84 has equivalent or better lives at 400 °C



Glenn Research Center at Lewis
Field

Life Prediction Branch:
where failure is not an option



Summary

- Large Extrusion has similar life to extruded bar
S-T orientation has shorter life due to stringers
Temperature effects are minimal on life
- Sheet has slightly poorer fatigue life
Temperature effect is larger
- AMZIRC has equivalent moderate temperature lives
Expect smaller lives at elevated temperatures
- Narloy-Z has equivalent lives at 20 and 400 C



Conclusions

- GRCop-84 has equivalent or better isothermal fatigue lives compared to other commercially available copper alloys
- GRCop-84 can be fabricated in various forms with minimal change in the fatigue lives
- GRCop-84 is equivalent in isothermal, fatigue to AMZIRC at moderate temperatures
- Narloy-Z is equivalent in fatigue capabilities to GRCop-84 at 400C and below

